

(19) Japan Patent Office (JP)

(12) Publication of Patent application (A)

(11) Patent Application Laid-Open Number

Japanese Patent Laid-Open Number: H9-63771

5 (43) Laid-Open Date: H9 (1997), March 7.

(51) Int. Cl. ⁶	Identification Mark	FI
H05B 33/26		H05B 33/26

10 Request for Examination: Not Filed. Number of claims: 7 OL (total 8 pages)

(21) Application Number

Patent Application Number: H7-217130

(22) Filing Date: H7 (1995), August 25.

15 (71) Applicant: 000003609

Toyota Central R&D Labs., Inc.

41-1, Aza Yokomichi, Oaza Nagakute, Nagakute-cho, Aichi-gun,

Aichi-ken

20 (72) Inventor: Tokitou Shizuo

c/o Toyota Central R&D Labs., Inc.

41-1, Aza Yokomichi, Oaza Nagakute, Nagakute-cho, Aichi-gun,

Aichi-ken

(72) Inventor: Noda Koji

25 c/o Toyota Central R&D Labs., Inc.

41-1, Aza Yokomichi, Oaza Nagakute, Nagakute-cho, Aichi-gun,

Aichi-ken

(72) Inventor: Taga Yasunori

c/o Toyota Central R&D Labs., Inc.

30 41-1, Aza Yokomichi, Oaza Nagakute, Nagakute-cho, Aichi-gun,

Aichi-ken

(74) Agent: Patent Attorney Yoshida Kenji (and two others)

(54) [Title of the Invention]

5 Organic Thin Film Light Emitting Element

(57) [Abstract]

[Object]

To provide an organic thin film light emitting element, in which light can be emitted at low voltage and luminous efficiency is high, by using a metal oxide thin film with a higher work function than that of indium tin oxide (ITO) for an anode to lower the energy barrier to a hole transporting layer or a light emitting layer.

[Solving Means]

In an organic thin film light emitting element, in which an anode 12 is formed on a substrate 10 and organic compound layers such as a hole transporting layer 18 and a light emitting layer 16, and a cathode 14 are formed thereover, the anode 12 is formed of a metal oxide thin film with a higher work function than that of ITO or a two-layer structure thin film with ITO.

[Scope of Claims]

[Claim 1]

20 An organic thin film light emitting element comprising:
an anode;
a cathode; and
one or a plurality of organic compound layers which are sandwiched therebetween,

25 characterized in that the anode is formed of a metal oxide thin film with a higher work function than that of indium tin oxide (ITO).

[Claim 2]

The organic thin film light emitting element as described in claim 1, characterized in that the anode has a two-layer structure of an ITO thin film having a film thickness ranging from 500 angstrom to 2000 angstrom and a metal oxide thin film

ranging from 50 angstrom to 300 angstrom.

[Claim 3]

The organic thin film light emitting element as described in claim 1, characterized in that the organic compound layer is a light emitting layer.

5 [Claim 4]

The organic thin film light emitting element as described in claim 1, characterized in that the organic compound layer comprises a hole transporting layer and a light emitting layer.

[Claim 5]

10 The organic thin film light emitting element as described in claim 1, characterized in that the organic compound layer comprises a light emitting layer and an electron transporting layer.

[Claim 6]

15 The organic thin film light emitting element as described in claim 1, characterized in that the organic compound layer comprises a hole transporting layer, a light emitting layer and an electron transporting layer.

[Claim 7]

20 The organic thin film light emitting element as described in claim 1, characterized in that the metal oxide is an oxide such as vanadium oxide, ruthenium oxide or molybdenum oxide in which a work function is higher than 4.6 eV.

[Detailed Description of the Invention]

[0001]

[Technical Field to which the Invention belongs to]

25 The present invention relates to a light emitting element which is used for a flat panel light emitting display, and particularly relates to an improvement of an organic thin film light emitting element using a fluorescent organic compound as a light emitting material.

[0002]

[Prior Art]

30 Recently, with progress to an information society, needs for low power

consumption and thin displays instead of the conventional CRT are growing. A liquid crystal display and a plasma display are noted as such a display, and they are already in practical use. However, needs of the age are still growing, and rather less power consumption and clearer full color displays are expected to be achieved.

5 [0003]

Nowadays, expectations for an organic thin film light emitting element using an organic compound are raised with these needs in the background. As an element structure which is reported so far, there is a structure in which one or a plurality of organic compound layers are sandwiched between an anode and a cathode, and
10 regarding the organic compound layer, there is a two-layer structure or a three-layer structure.

[0004]

As an example of the two-layer structure, there is a structure in which a hole transporting layer and a light emitting layer are formed between an anode and a cathode
15 (Laid-Open No. S59-194393, Appl. Phys. Lett. 51,913(1987)), or a structure in which a light emitting layer and an electron transporting layer are formed between an anode and a cathode (USP No. 5,085947, Laid-Open No. H2-250952, Appl. Phys. Lett. 55, P1489 (1989)). Additionally, as an example of the three-layer structure, a structure in which a hole transporting layer, a light emitting layer and an electron transporting layer are
20 formed between an anode and a cathode (Appl. Phys. Lett. 57,531(1990)) is noted. Further, a single layer structure in which a single layer has all functions by using a high molecule and a mixed system (Nature, 345,539(1990), Appl. Phys. Lett. 61,761(1992)) is also reported. These element structures are shown in FIGS. 6, 7, 8 and 9.

[0005]

25 FIG. 6 shows an example of the single layer structure in which a light emitting layer 16 which is a single organic compound layer is formed between an anode 12 provided on a substrate 10 and a cathode 14. In this case, the light emitting layer 16 also serves as a hole transporting layer and an electron transporting layer.

[0006]

30 FIG. 7 shows an example of the two-layer structure in which a light emitting

layer 16 and a hole transporting layer 18 which are organic compound layers are formed between an anode 12 provided on a substrate 10 and a cathode 14. In this case, the light emitting layer 16 also serves as an electron transporting layer.

[0007]

5 FIG 8 shows an example of the two-layer structure in which a light emitting layer 16 and an electron transporting layer 20 which are organic compound layers are formed between an anode 12 provided on a substrate 10 and a cathode 14. The light emitting layer 16 also serves as a hole transporting layer in this case.

[0008]

10 FIG 9 shows an example of the three-layer structure in which a light emitting layer 16, a hole transporting layer 18 and an electron transporting layer 20 which are organic compound layers are formed between an anode 12 provided on a substrate 10 and a cathode 14.

[0009]

15 A light emission mechanism in these organic thin film light emitting elements is as follows: A hole injected from the anode and an electron injected from the cathode reach the light emitting layer 16 through the hole transporting layer 18 or the electron transporting layer 20, and they are recombined there to achieve an excited state of an organic compound which composes the light emitting layer 16. When the excited state
20 returns to a ground state, light of the same wavelength as the fluorescence of the organic compound is emitted.

[0010]

25 An organic compound used as a material for the light emitting layer is a material which exhibits strong fluorescence. So far, various organic compounds are reported as materials that can be used for the hole transporting layer 18, the light emitting layer 16 and the electron transporting layer 20. For example, aromatic tertiary amine is reported as a material for the hole transporting layer 18.

[0011]

30 In addition, as a material for the light emitting layer 16, aluminum trisoxine which is expressed in the chemical formula below (Laid-Open No. S59-194393, Laid

Open No. S63-295695)

[Chemical formula 1],

a styryl amine derivative and a styryl benzene derivative (Laid-Open No. H2-209988) are reported.

5 [0012]

Additionally, as a material for the electron transporting layer 20, an oxadiazole derivative and the like (Appl. Phys. Lett. 63,2032 (1993)) are reported.

[0013]

There are many reported examples not only as for these low-molecular weight
10 compounds but also as for a high-molecular weight compound. In particular, as for a poly (P-phenylenevinylene) based derivative (Nature, 347,539(1990)), favorable properties are obtained even in the single layer structure element.

[0014]

The capability of an organic thin film light emitting element using these
15 materials is sufficiently on the practical level as a light emitting element from the aspect of a luminescent color and brightness thereof.

[0015]

[Problem to be solved by the Invention]

However, these organic thin film light emitting elements have been not yet in
20 practical use. The major reason is that the durability of the element is low.

[0016]

So far, high luminance of several thousands cd/m^2 is achieved in the initial
stages by a direct current voltage of approximately 10 V by applying various element
structures and organic compounds. However, property deterioration such as a
25 luminance decrease or a drive voltage increase occurs due to continuous driving or a long storage, which prevents a practical use of the organic thin film light emitting element. Several factors that control this element lifetime are reported, although it was considered heretofore that the heat resistance of the thin film was a major factor. Therefore, in order to stabilize a film structure of the organic compound layer, it is
30 attempted to synthesize an organic compound that is superior in heat stability, namely,

in which the softening temperature (T_g) or the melting point is high (Appl. Phys. Lett 61, 2503 (1992)).

[0017]

However, according to systematic experiments in which a triphenyldiamine
5 derivative of the aromatic tertiary amine expressed by the chemical formula bellow
[Chemical Formula 2]

is focused, it is reported recently that the element lifetime is more related to an
ionization potential of a hole transporting layer than to the softening temperature or the
melting point (Appl. Phys. Lett., 66.2679 (1995)). This means that the element
10 lifetime is longer as the energy barrier between indium tin oxide (ITO) that is an anode
and a hole transporting layer, namely, an energy difference between Fermi level of the
ITO electrode and a highest occupied level of the hole transporting layer, is smaller.

[0018]

Generally, it is known that Fermi level of the ITO electrode is 4.6 eV (Nature,
15 Vol.370, 354 (1994)), and this value corresponds to the work function. In addition, it
is known that the highest occupied level of triphenyldiamine (TPD) that is a typical
diamine derivative used for the hole transporting layer is 5.5 eV (Appl. Phys. Lett., 61,
2503 (1992)), and this value corresponds to the ionization potential.

[0019]

20 In the case where the TPD is used for the hole transporting layer, there is a
barrier of approximately 0.9 eV between the ITO electrode and the hole transporting
layer for a hole carrier. When this energy difference is small, exothermic heat of the
element can be suppressed without having to apply too much voltage to the barrier
portion. It is attempted to synthesize a material with a larger ionization potential using
25 many diamine derivatives, however, there is a limit in lowering the barrier only by an
approach using an organic material. Therefore, it is expected to develop a transparent
electrode with the higher work function than that of the conventional ITO by improving
an electrode material.

[0020]

30 Note that the energy barrier between an anode and a light emitting layer is a

problem in an element in which a light emitting layer also serves as a hole transporting layer. For example, there is a barrier of 0.4 eV in the case of poly (P-phenylenevinylene) with an ionization potential of 5.0 eV (Nature, 370, 354 (1990)).

[0021]

5 The present invention is made in view of the conventional problems described above, and the object is to provide an organic thin film light emitting element in which drive voltage can be lowered, light emission capability can be kept for a long time and the durability is high by lowering the energy barrier to a hole transporting layer or a light emitting layer using a metal oxide thin film with the higher work function than that of ITO which is the conventional anode material.

[0022]

[Means to solve the Problem]

 In the invention as described in claim 1, an organic thin film light emitting element comprising an anode, a cathode and one or a plurality of organic compound
15 layers which are sandwiched therebetween is characterized in that the anode is formed of a metal oxide thin film with the higher work function than that of indium tin oxide (ITO) in order to achieve the object described above.

[0023]

 In the invention as described in claim 2, the organic thin film light emitting
20 element as described in claim 1 is characterized in that the anode has a two-layer structure of an ITO thin film having a film thickness ranging from 500 angstrom to 2000 angstrom and a metal oxide thin film ranging from 50 angstrom to 300 angstrom.

[0024]

 In the invention as described in claim 3, the organic thin film light emitting
25 element as described in claim 1 is characterized in that the organic compound layer is a light emitting layer.

[0025]

 In the invention as described in claim 4, the organic thin film light emitting element as described in claim 1 is characterized in that the organic compound layer
30 comprises a hole transporting layer and a light emitting layer.

[0026]

In the invention as described in claim 5, the organic thin film light emitting element as described in claim 1 is characterized in that the organic compound layer comprises a light emitting layer and an electron transporting layer.

5 [0027]

In the invention as described in claim 6, the organic thin film light emitting element as described in claim 1 is characterized in that the organic compound layer comprises a hole transporting layer, a light emitting layer and an electron transporting layer.

10 [0028]

In the invention as described in claim 7, the organic thin film light emitting element as described in claim 1 is characterized in that the metal oxide is an oxide such as vanadium oxide, ruthenium oxide or molybdenum oxide in which the work function is higher than 4.6 eV.

15 [0029]

[Embodiments of the Invention]

Hereinafter, preferable embodiments of the present invention are described based on the drawings.

[0030]

20 FIG. 1 shows a cross-sectional view of an organic thin film light emitting element according to the present invention. In FIG. 1, an anode 12 is formed on a substrate 10 formed of glass or the like, a hole transporting layer 18 of TPD is formed on the anode 12, a light emitting layer 16 of an aluminum-quinolinol complex (Alq) is formed on the hole transporting layer 18 and a cathode 14 of an MgAg alloy is formed on the light emitting layer 16.

25

[0031]

As the anode 12, a material in which the work function is higher than that of ITO that is the conventional anode material and the conductivity is high is used. For instance, ruthenium oxide (RuO_x), molybdenum oxide (MoO_x) or vanadium oxide (VO_x) or the like is preferable.

30

[0032]

In Table 1, examples of the work function of each metal oxide thin film are shown. These values are measured by the atmospheric ultraviolet photoelectron spectroscopy. The work function of the metal oxide thin film shown in Table 1 is a
 5 higher value than that of ITO, and thus it can be used as the anode material for the organic thin film light emitting element according to the present invention.

[0033]

[Table 1]

Metal Oxide Thin Film	Work function (eV)
RuOx	4.9
MoOx	5.4
VOx	5.4
ITO	4.6

A metal oxide thin film with limited optical transparency among these metal
 10 oxide thin films is made to be a two-layer structure electrode with ITO. An example thereof is shown in FIG. 2. In FIG. 2, an ITO layer 22 is formed on a substrate 10, a metal oxide thin film 24 is formed on the ITO layer 22, and thus a two-layer structure anode 12 is composed. Note that a predetermined organic compound layer and a cathode are formed over the metal oxide thin film 24, however, the illustration thereof is
 15 omitted here.

[0034]

When the anode has the two-layer structure, the film thickness of the metal oxide thin film 24 is preferably less than or equal to 300 angstrom and equal to or more than 50 angstrom. The film thickness of the ITO is set to be in a range from 500
 20 angstrom to 2000 angstrom. The metal oxide thin film may be manufactured by electron beam deposition, a direct current sputtering method, an RF-magnetron sputtering method, an ICB deposition method or the like, namely, a manufacturing method thereof is not limited as long as it is used to manufacture the oxide thin film.

[0035]

25 An organic compound which can be used in the present invention is not limited

to the one shown in FIG. 1, but all the known materials can be applied. For example, as a material for the hole transporting layer, aromatic tertiary amine (USP No. 4, 175, 960, USP No. 4, 539, 507, Phil. Mag. B, 53, 193 (1986)), a phthalocyanine derivative, and a pyrazoline derivative are noted, and particularly, the aromatic tertiary amine is the most effective compound. As a material for the light emitting layer, a metal chelated oxinoid compound (Laid-Open No.S59-194393), an oxadiazole derivative, a butadiene derivative, a perylene derivative, a styrylbenzene derivative (Laid-Open No.H2-247277), a perynone derivative and the like are noted. As a material for the electron transporting layer, an oxadiazole compound (Appl. Phys. Lett. 55, 1489 (1989)), a butadiene derivative, a perylene derivative and the like are noted, and, additionally, a metal chelated oxinoid compound (Laid-Open No.S59-194393) can be also used.

[0036]

As a cathode material, silver, tin, magnesium, aluminum, calcium in each of which the work function is low, or an alloy thereof are used. In addition, zinc oxide doped with aluminum or germanium can be also used as a transparent cathode. At least one of the anode and the cathode is preferably sufficiently transparent in a light emission wavelength region of the element.

[0037]

As shown in FIG. 1, the organic thin film light emitting element according to the present invention is composed as an element by laminating each layer described above in sequence on a glass substrate or a semiconductor substrate of silicon or the like. They may be sealed in a glass cell with silicon oil or the like for element stability, particularly for protection against moisture in the air.

[0038]

Note that the organic thin film light emitting element according to the present invention is not limited to the structure shown in FIG. 1, and it may also have a structure shown in FIG. 6, 7, 8 or 9 if necessary.

[0039]

Hereinafter, a specific example of the organic thin film light emitting element according to the present invention is described more in detail by embodiments.

[0040]

[Embodiments]

Embodiment 1. A manufacturing method of a metal oxide thin film and a property thereof are described in the present embodiment.

5 [0041]

A metal oxide thin film is formed by a radio-frequency magnetron sputtering method on a glass substrate by using each material shown in Table 1. A forming condition and a property of this metal oxide thin film are shown in Table 2.

[0042]

10 [Table 2]

Metal oxide thin film	Forming condition		Typical composition	Film Thickness (Å)	Resistivity (Ω cm)	Light Transmittance (%)
	Target	Sputtering Gas				
RuOx	Ru	Ar(70%) + O ₂ (30%)	RuO _{1.92}	3680	2.7×10^{-4}	10
MoOx	MoO ₃	Ar	MoO ₃	2150	1.2×10^{-2}	10
VOx	V ₂ O ₅	Ar	VO _{2.22}	1320	10^5	20
ITO	ITO(5wt%SnO ₂)	Ar(99%) + O ₂ (1%)		1720	3.3×10^{-4}	90

The substrate temperature is set to be 150 °C, and sputtering gas pressure is set to be 2×10^{-3} Torr (0.27 Pa). A molybdenum oxide thin film and a ruthenium oxide thin film indicate high conductivity, and a vanadium oxide thin film is semiconducting. These metal oxide thin films are colored and optical transparency thereof in a visible range is low as shown in Table 2, thus, it is preferable that they have the two-layer structure with ITO as described above. In Table 2, a typical composition of each metal oxide thin film is also indicated as a reference. This composition is slightly changed

depending on a condition of film formation by sputtering (gas pressure, gas type).

[0043]

Table 3 shows conductivity and light transmittance of a two-layer structure electrode as shown in FIG. 2 in which ITO and the metal oxide thin film are laminated.

- 5 The film thickness of the metal oxide thin film is set to be less than or equal to 300 angstrom in order to increase transparency. In addition, the film thickness of ITO is set to be 1200 angstrom.

[0044]

- 10 In the present embodiment, the surface resistance can be set to be approximately $25 \Omega/\square$ by the electrode having the two-layer structure. Further, the light transmittance can be higher than the value of each metal oxide thin film shown in FIG. 2.

[0045]

[Table 3]

Transparent Electrode	Surface Resistance (Ω/\square)	Transmittance (%)
RuOx/ITO	22.5	60
MoOx/ITO	29.1	40
VOx/ITO	33	60
ITO	20	90

- 15 Embodiment 2. In the present embodiment, an organic thin film light emitting element having a structure shown in FIG. 1 is manufactured and its properties are evaluated.

[0046]

- 20 An anode of a vanadium oxide thin film of approximately 1500 angstrom is formed on a glass substrate by the method of the embodiment 1. TPD of approximately 500 angstrom is formed as a hole transporting layer on the anode by a vacuum deposition method under a condition where vacuum degree is approximately 2×10^{-7} Torr (2.7×10^{-5} Pa) and deposition rate is approximately 30 angstrom/minute. As a light emitting layer, an aluminum quinolinol complex is used. As a cathode, an alloy of Mg and Ag (Mg:Ag = 10:1) of approximately 1800 angstrom is formed under a

condition where vacuum degree is 1×10^{-6} Torr (1.3×10^{-4} Pa) and deposition rate is approximately 150 angstrom/minute. The size of one element is 3 mm \times 3 mm, and 15 elements are manufactured on a substrate of 25 mm \times 35 mm.

[0047]

- 5 A direct-current voltage is applied to an organic thin film light emitting element which is manufactured as described above so that an anode of the organic thin film light emitting element is positive and a cathode of that is negative. When light emission from a glass substrate side is observed, green light emission of 1 cd/m² is started by applied voltage of 3V, and the green light emission is observed for a long time.
- 10 Therefore, when the applied voltage by which luminance of 1 cd/m² is obtained is defined as a light emission starting voltage, the light emission starting voltage of the element of the present embodiment is 3 V. Further, luminance of 20 cd/m² is observed when 5 V is applied. The highest luminance is 300 cd/m² by the applied voltage of 12 V.

15 [0048]

Comparative Example 1.

- ITO of 1500 angstrom is formed as an anode on a glass substrate by a radio frequency magnetron sputtering method, and thereover, a hole transporting layer, a light emitting layer and an MgAg electrode are vacuum-deposited by the same method as the
- 20 embodiment 2 in order to manufacture an element for comparison. In this element for comparison, the applied voltage by which luminance of 1 cd/m² is obtained; namely, the light emission starting voltage is 5 V. The capability is obtained that the highest luminance is 5000 cd/m² by the applied voltage of 15 V. Luminous efficiency is approximately 0.85 lm/W by drive current of 10 mA/cm². When the emission lifetime
- 25 of this element is measured under a drive condition of 10 mA/cm², a half lifetime (a time in which the initial luminance is halved) is 80 hours as shown in FIG. 4.

[0049]

Comparative Example 2.

- In₂O₃ of 1500 angstrom is formed on a glass substrate by a radio frequency
- 30 magnetron sputtering method, and thereover, a hole transporting layer, a light emitting

layer and an MgAg electrode are vacuum-deposited by the same method as the embodiment 2 in order to manufacture an element for comparison. In this element for comparison, the light emission starting voltage by which luminance of 1 cd/m^2 is obtained is 7 V, and the highest luminance is 4000 cd/m^2 by the applied voltage of 15 V.

5 [0050]

Comparative example 3.

SnO_2 of 1500 angstrom is formed on a glass substrate by a radio frequency magnetron sputtering method, and thereafter, a hole transporting layer, a light emitting layer and an MgAg electrode are vacuum-deposited by the same method as the
10 embodiment 2. In this element, the light emission starting voltage by which luminance of 1 cd/m^2 is obtained is 7 V, and the highest luminance is 4000 cd/m^2 by the applied voltage of 15 V.

[0051]

When the embodiment 2 and the comparative examples 1, 2, 3 are compared, it
15 is understood that the light emission starting voltage is lowered in the element according to the present invention. However, since the light transparency of the vanadium oxide electrode is low, sufficient luminance cannot be achieved. Therefore, an embodiment of a two-layer electrode in which the light transparency is improved by laminating with an ITO thin film is shown as follows.

20 [0052]

Embodiment 3.

ITO of 1200 angstrom and a vanadium oxide thin film of 300 angstrom are formed continuously over a glass substrate by a radio frequency magnetron sputtering method in order to form a two-layer structure electrode (transparent electrode). Over
25 this electrode, as in the embodiment 2, a hole transporting layer of approximately 500 angstrom, a light emitting layer of approximately 500 angstrom and an MgAg electrode of approximately 1800 angstrom are formed to manufacture an organic thin film light emitting element. A result of measuring the light emission starting voltage and the luminous efficiency of this organic thin film light emitting element is shown in Table 4.

30 [0053]

[Table 4]

	Transparent Electrode	Light Emission Starting Voltage (V)	Luminous Efficiency (lm/W)
Embodiment 3	VOx/ITO	3	0.92
Embodiment 4	RuOx/ITO	3.5	0.85
Embodiment 5	MoOx/ITO	3.5	0.80
Conventional Example	ITO	5	0.85

As shown in Table 4, the light emission starting voltage of this element is 3 V.

- 5 In addition, as shown in FIG. 5, luminance of 100 cd/m^2 is observed when only 5 V is applied. The highest luminance is 5000 cd/m^2 by 12 V, and the luminous efficiency is 0.92 lm/W (drive current 10 mA/cm^2). When the half lifetime of this element is measured under a drive condition of 10 mA/cm^2 , it is over 100 hours as shown in FIG. 4. It is understood that strong light can be emitted by lower applied voltage and the luminous efficiency is improved, besides, the emission lifetime is longer, as compared with an element using only ITO.

[0054]

- Further, in the case of a two-layer structure electrode in which the vanadium oxide thin film is set to be 100 angstrom, the light emission starting voltage is 3 V and it is not different from the above described example, however, the highest luminance is increased and the luminous efficiency is 1.0 lm/W .

[0055]

Embodiment 4.

- Over a two-layer structure electrode in which ITO of 1400 angstrom and a ruthenium oxide thin film of 300 angstrom are formed over a glass substrate, a hole transporting layer of approximately 500 angstrom, a light emitting layer of approximately 500 angstrom and an MgAg electrode of approximately 1800 angstrom are formed as in the embodiment 2 in order to manufacture an organic thin film light

emitting element, and the light emission starting voltage and the luminous efficiency are measured as in the embodiment 3.

[0056]

The light emission starting voltage of this element is 3.5 V as shown in Table 4.

5 Additionally, luminance of 30 cd/m^2 is observed when 5 V is applied (FIG. 4). The luminous efficiency is 0.85 lm/W.

[0057]

In the present embodiment, if the film thickness of the ruthenium oxide is made further thinner, the light transmittance of the electrode is improved, and thus the efficiency is further improved.

[0058]

Embodiment 5.

Over a two-layer structure electrode in which ITO of 1200 angstrom and molybdenum oxide of 300 angstrom are formed continuously over a glass substrate, a hole transporting layer, a light emitting layer and an electrode are vacuum-deposited as in the embodiment 2 in order to manufacture an organic thin film light emitting element, and the light emission starting voltage and the luminous efficiency are measured as in the embodiment 3.

[0059]

20 As shown in Table 4, the light emission starting voltage of this element is 3.5 V, and the luminance is 30 cd/m^2 by the applied voltage of 5 V (FIG. 5).

[0060]

Embodiment 6.

Next, an embodiment of an element in which light is taken from an upper electrode (cathode) is shown.

[0061]

FIG. 3 shows a cross-sectional view of an organic thin film light emitting element according to the present embodiment. In FIG. 3, ruthenium oxide of 1500 angstrom is formed as an anode 12 on a glass substrate 10, and thereafter, a hole transporting layer 18 and a light emitting layer 16 are vacuum-deposited as in the

embodiment 2. Finally, as a cathode 14, aluminum-doped zinc oxide of approximately 1200 angstrom whose work function is low is formed by a radio frequency sputtering method.

[0062]

5 When plus voltage is applied to the ruthenium oxide electrode (the anode 12) in this element and light is observed through the zinc oxide electrode (the cathode 14), clear light emission is observed from the transparent cathode 14 side. In this case, light emission with a higher contrast ratio than in the case of the MgAg metal electrode is obtained since the ruthenium oxide electrode is black in color.

10 [0063]

[Effect of the Invention]

As described above, according to the present invention, the energy barrier between a metal oxide thin film electrode and a hole transporting layer or a light emitting layer can be small so that a hole is easily injected into the hole transporting
15 layer or the light emitting layer and the element can be driven by lower applied voltage. As a result, luminous efficiency is improved and a longer lifetime of the element is achieved. Therefore, the light emitting element of the present invention can be applied to various display fields.

[Brief Description of the Drawings]

20 [FIG. 1] A cross-sectional view of an organic thin film light emitting element according to the present invention.

[FIG. 2] A cross-sectional view of a two-layer structure electrode according to the present invention.

25 [FIG. 3] A cross-sectional view of an organic thin film light emitting element in which light is taken from a cathode according to the present invention.

[FIG. 4] A diagram showing luminance change corresponding to a drive time of various elements.

[FIG. 5] A diagram showing the relationship between applied voltage and luminance of various elements.

30 [FIG. 6] A cross-sectional view of an organic thin film light emitting element having a

single layer structure.

[FIG. 7] A cross-sectional view of a two-layer structure organic thin film light emitting element having a hole transporting layer.

[FIG. 8] A cross-sectional view of a two-layer structure organic thin film light emitting element having an electron transporting layer.

[FIG. 9] A cross-sectional view of a three-layer structure organic thin film light emitting element.

[Explanation of Reference Numerals]

- 10 Substrate
- 10 12 Anode
- 14 Cathode
- 16 Light emitting layer
- 18 Hole transporting layer
- 20 Electron transporting layer
- 15 22 ITO layer
- 24 Metal oxide thin film

(51) IntCl.⁴
H 0 5 B 33/26

識別記号 庁内整理番号

F I
H 0 5 B 33/26

技術表示箇所

審査請求 未請求 請求項の数7 O L (全 8 頁)

(21) 出願番号 特願平7-217130

(22) 出願日 平成7年(1995)8月25日

(71) 出願人 000003609

株式会社豊田中央研究所
愛知県愛知郡長久手町大字長湫字横道41番
地の1

(72) 発明者 時任 勝士

愛知県愛知郡長久手町大字長湫字横道41番
地の1 株式会社豊田中央研究所内

(72) 発明者 野田 浩司

愛知県愛知郡長久手町大字長湫字横道41番
地の1 株式会社豊田中央研究所内

(72) 発明者 多賀 康剛

愛知県愛知郡長久手町大字長湫字横道41番
地の1 株式会社豊田中央研究所内


(74) 代理人 弁理士 吉田 研二 (外2名)

(54) 【発明の名称】 有機薄膜発光素子

(57) 【要約】

【課題】 仕事関数がインジウム錳酸化物 (ITO) よりも大きな金属酸化物薄膜を陽極に用いることで、正孔輸送層あるいは発光層とのエネルギー障壁を低減させ、低電圧で発光可能でかつ発光効率が高い有機薄膜発光素子を提供する。

【解決手段】 基板10上に陽極12が形成され、その上に正孔輸送層18、発光層16等の有機化合物層及び陰極14が形成されている有機薄膜発光素子であって、陽極12が、仕事関数がITOよりも大きな金属酸化物薄膜あるいはITOとの2層構造薄膜により形成されている。



【特許請求の範囲】

【請求項 1】 陽極および陰極と、これらに挟まれた 1 層または複数層の有機化合物層より構成される有機薄膜発光素子において、前記陽極が、仕事関数が酸化錫インジウム (ITO) よりも大きな金属酸化物薄膜からなることを特徴とする有機薄膜発光素子。

【請求項 2】 請求項 1 記載の有機薄膜発光素子において、前記陽極を、膜厚 500 オングストロームから 2000 オングストロームの範囲の ITO 薄膜と 50 オングストロームから 300 オングストロームの範囲の金属酸化物薄膜とにより 2 層構造としたことを特徴とする有機薄膜発光素子。

【請求項 3】 請求項 1 記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層であることを特徴とする有機薄膜発光素子。

【請求項 4】 請求項 1 記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層と発光層とからなることを特徴とする有機薄膜発光素子。

【請求項 5】 請求項 1 記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層と電子輸送層とからなることを特徴とする有機薄膜発光素子。

【請求項 6】 請求項 1 記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層と発光層と電子輸送層とからなることを特徴とする有機薄膜発光素子。

【請求項 7】 請求項 1 記載の有機薄膜発光素子において、前記金属酸化物は、酸化バナジウム、酸化ルテウム、酸化モリブデンなどの仕事関数が 4.6 eV よりも大きな酸化物であることを特徴とする有機薄膜発光素子。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】 本発明は平面発光ディスプレイに用いる発光素子に関するものであり、特に発光物質として蛍光性有機化合物を利用した有機薄膜発光素子の改良に関するものである。

【0002】

【従来の技術】 近年、情報社会の進歩に伴い、従来の CRT よりも低消費電力でかつ薄型のディスプレイへのニーズが高まっている。この様なディスプレイとしては液晶ディスプレイやプラズマディスプレイがあり、すでに実用化されている。しかし、時代のニーズはさらに高度化し、さらに低消費電力化、鮮明なフルカラー化が望まれている。

【0003】 最近、それらのニーズを背景に、有機化合物を利用した有機薄膜発光素子への期待が高まっている。これまでに報告されている素子の構造としては、陽極および陰極の間に 1 層または複数層の有機化合物層が挟まれた構造となっており、有機化合物層としては 2 層構造あるいは 3 層構造がある。

【0004】 2 層構造の例としては、陽極と陰極との間

に正孔輸送層と発光層が形成された構造 (特開昭 59-194393、Appl. Phys. Lett. 51, 913 (1987)) 又は陽極と陰極との間に発光層と電子輸送層とが形成された構造 (USP No. 5, 085,947、特開平 2-250952、Appl. Phys. Lett. 55, P1489 (1989)) がある。また、3 層構造の例としては、陽極と陰極との間に正孔輸送層と発光層と電子輸送層とが形成された構造 (Appl. Phys. Lett. 57, 531 (1990)) がある。また、単一層に全ての役割を持たせた単層構造 (Nature, 347, 539 (1990)、Appl. Phys. Lett. 61, 761 (1992)) も高分子や混合系で報告されている。これらの素子構造が図 6, 7, 8, 9 に示される。

【0005】 図 6 には、基板 10 上に設けられた陽極 12 と陰極 14 との間に単一の有機化合物層である発光層 16 が形成された単層構造の例が示される。この場合の発光層 16 は、正孔輸送層及び電子輸送層の機能も果たしている。

【0006】 図 7 には、基板 10 上に設けられた陽極 12 と陰極 14 との間に有機化合物層である発光層 16 と正孔輸送層 18 とが形成された 2 層構造の例が示される。この場合の発光層 16 は、電子輸送層の機能も果たしている。

【0007】 図 8 には、基板 10 上に設けられた陽極 12 と陰極 14 との間に有機化合物層である発光層 16 と電子輸送層 20 とが形成された 2 層構造の例が示される。この場合の発光層 16 は、正孔輸送層の機能も果たしている。


【0008】 図 9 には、基板 10 上に設けられた陽極 12 と陰極 14 との間に有機化合物層である発光層 16 と正孔輸送層 18 と電子輸送層 20 とが形成された 3 層構造の例が示される。

【0009】 これら有機薄膜発光素子における発光メカニズムは、陽極から注入された正孔と陰極から注入された電子とが、正孔輸送層 18 あるいは電子輸送層 20 を介して発光層 16 に到達し、そこで再結合することによって発光層 16 を構成する有機化合物の励起状態を作り出し、その励起状態が基底状態に戻るときに有機化合物の蛍光と同じ波長の光を放出するというものである。

【0010】 発光層用材料として用いられる有機化合物は強い蛍光性を示す材料である。上記正孔輸送層 18、発光層 16、電子輸送層 20 に使用可能な材料としては、これまで様々な有機化合物が報告されている。たとえば、正孔輸送層 18 の材料としては、芳香族 3 級アミンが報告されている。

【0011】 また、発光層 16 の材料としては、以下の化学式で表されるアルミニウムトリオキシン (特開昭 59-194393、特開昭 63-295695)

【化 1】



や、ステリルアミン誘導体、スチリルベンゼン誘導体（特開平2-209988）が報告されている。

【0012】また、電子輸送層20の材料としては、オキサジアゾール誘導体等（Appl. Phys. Lett. 63, 2032（1993））が報告されている。

【0013】これら低分子量の化合物ばかりではなく、高分子量の化合物でも多くの報告例があり、特にポリ（P-フェニレンビニレン）系誘導体（Nature, 347, 539（1990））は、単層構造の素子でも良好な特性が得られている。

【0014】これらの材料を使用した有機薄膜発光素子は、その発光色や明るさから見て、発光素子としての性能は十分に実用レベルにある。


【0015】

【発明が解決しようとする課題】しかし、これら有機薄膜発光素子は未だ実用に至っていない。その最大の原因は素子の耐久性が乏しいことにある。

【0016】これまで、様々な素子構造および有機化合物を採用することにより、初期的には数1000cd/m²の高輝度が直流電圧10V程度で達成されているが、連続駆動あるいは長期保存によって輝度の低下と駆動電圧の上昇といった特性の変化が起り、これが有機薄膜発光素子の実用化を妨げている。この素子寿命を支配している要因は幾つか報告されているが、従来は荷電の耐熱性がその主要原因であると考えられていた。そのため、有機化合物層の膜構造を安定化させるために、熱安定性に優れた、つまり軟化温度（T_g）や融点の高い有機化合物の合成が試みられている（Appl. Phys. Lett. 61, 2503（1992））。

【0017】しかし最近、以下の化学式で表される芳香族3級アミンのトリフェニルジメチルアミン誘導体

【化2】



を中心にした系統的な実験から、素子の寿命はこれら軟化温度や融点よりも正孔輸送層のイオン化ポテンシャルに関係していることが報告されている（Appl. Phys. Lett., 66, 2679（1995））。これは、陽極である酸化錫インジウム（ITO）と正孔輸

送層のエネルギー障壁すなわちITO電極のフェルミ準位と正孔輸送層の最高占有準位のエネルギー差が小さいほど素子の寿命が長くなることを意味している。

【0018】一般に、ITO電極のフェルミ準位は4.6eV（Nature, Vol. 370, 354（1994））であることが知られており、この値は仕事関数に対応している。また、正孔輸送層に使用される代表的なジメチルアミン誘導体であるトリフェニルジメチルアミン（TPD）の最高占有準位は5.5eV（Appl. Phys. Lett., 61, 2503（1992））であることが知られており、この値はイオン化ポテンシャルに対応している。

【0019】上述のTPDを正孔輸送層に使用する場合、正孔キャリアにとってはITO電極と正孔輸送層との間に約0.9eVの障壁が存在することになる。このエネルギー差が小さければ障壁部に無理な電圧がかかる必要がなく、素子の発熱が抑えられる。多くのジメチルアミン誘導体でイオン化ポテンシャルの大きな材料の合成が試みられているが、有機材料からのアプローチだけでは障壁低減に限界がある。従って、電極材料を改良して、従来のITOよりも仕事関数の大きな透明電極を開発することが望まれている。

【0020】尚、発光層が正孔輸送層の機能も果たしている型の素子の場合、陽極と発光層との間のエネルギー障壁が問題となる。例えば、イオン化ポテンシャルが5.0eVのポリ（P-フェニレンビニレン）の場合、0.4eVの障壁が存在することになる（Nature, 370, 354（1990））。

【0021】本発明は上記従来の課題に鑑みながらなされたものであり、その目的は、仕事関数が従来の陽極材料であるITOよりも大きい金属酸化化合物薄膜を用いて正孔輸送層あるいは発光層とのエネルギー障壁を低減させ、駆動電圧が低下でき発光性能が長時間に亘って保持できる耐久性に優れた有機薄膜発光素子を提供することにある。

【0022】

【課題を解決するための手段】上記目的を達成するために、請求項1記載の発明は、陽極および陰極と、これらに挟まれた1層または複数層の有機化合物層より構成される有機薄膜発光素子において、前記陽極が、仕事関数が酸化錫インジウム（ITO）よりも大きな金属酸化化合物薄膜からなることを特徴とする。

【0023】請求項2記載の発明は、請求項1記載の有機薄膜発光素子において、前記陽極を、膜厚500オングストロームから2000オングストロームの範囲のITO薄膜と500オングストロームから300オングストロームの範囲の金属酸化化合物薄膜とにより2層構造としたことを特徴とする。

【0024】請求項3記載の発明は、請求項1記載の有機薄膜発光素子において、前記有機化合物層が発光層であることを特徴とする。

【0025】請求項4記載の発明は、請求項1記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層と発光層とからなることを特徴とする。

【0026】請求項5記載の発明は、請求項1記載の有機薄膜発光素子において、前記有機化合物層が発光層と電子輸送層とからなることを特徴とする。

【0027】請求項6記載の発明は、請求項1記載の有機薄膜発光素子において、前記有機化合物層が正孔輸送層と発光層と電子輸送層とからなることを特徴とする。

【0028】請求項7記載の発明は、請求項1記載の有機薄膜発光素子において、前記有機化合物層は、酸化バナジウム、酸化ルテニウム、酸化モリブデンなどの仕事関数が4.6 eVよりも大きな酸化物であることを特徴とする。

【0029】

【発明の実施の形態】以下、本発明の好適な実施の形態を図面に基づいて説明する。

【0030】図1には、本発明に係る有機薄膜発光素子の断面図が示される。図1において、ガラス等の基板1

0の上に陽極12が形成され、陽極12の上にTPDからなる正孔輸送層18が形成され、正孔輸送層18の上にアルミニウムノール錯体(Alq)からなる発光層16が形成され、発光層16の上にMgAg合金からなる陰極14が形成されている。

【0031】陽極12としては、従来の陽極材料であるITOよりも仕事関数が大きく導電性が高い材料が使用される。たとえば、ルテニウム酸化物(RuO_4)、モリブデン酸化物(MoO_4)、バナジウム酸化物(VO_4)などが好ましい。

【0032】表1には、各金属酸化物薄膜の仕事関数の例が示される。これらの値は、大気中紫外光電子分光法で実測したものである。表1に示された金属酸化物薄膜の仕事関数は、ITOよりも大きな値となっており、本発明に係る有機薄膜発光素子の陽極材料として使用が可能である。

【0033】

【表1】

金属酸化物 薄膜	仕事関数 (eV)
RuO_4	4.9
MoO_4	5.4
VO_4	5.4
ITO	4.6

これらの金属酸化物薄膜の中で光の透過性の乏しいものはITOとの2層構造の電極とする。この例が図2に示される。図2においては、基板10の上にITO層22が形成され、ITO層22の上に金属酸化物薄膜24が形成されて2層構造の陽極12が構成されている。尚、金属酸化物薄膜24の上には所定の有機化合物層及び陰極が形成されているが図示は省略した。

【0034】陽極を2層構造とした場合の金属酸化物薄膜24の膜厚は300オングストローム以下で500オングストローム以下が好ましい。ITOの膜厚は500オングストロームから2000オングストロームの範囲とする。金属酸化物薄膜の作製は、電子ビーム蒸着、直流スパッタ法、RFマグネトロンスパッタ法、ICB蒸着法など、酸化物薄膜を作製するのに用いられる方法であれば、その作製方法は限定されない。

【0035】本発明に用いることができる有機化合物は、図1に示されたものだけではなく、従来公知の材料すべてが適用される。たとえば、正孔輸送層材料としては、芳香族3級アミン(USP No. 4, 175, 960, USP No. 4, 539, 507, Phil. Mag. B, 53, 193 (1986))、フタロシアニン誘導体やピラゾリン誘導体が挙げられ、特に芳香族

3級アミンは最も有用な化合物である。発光層用材料としては、金属キレート化オキシニド化合物(特開昭59-194393)、オキサジアンゾール誘導体、ブタジエン誘導体、ペリレン誘導体、スチリベンゼン誘導体(特開平2-247277)、ペリノン誘導体等が挙げられる。電子輸送層材料としては、オキサジアンゾール化合物(Appl. Phys. Lett. 55, 1489 (1989))、ブタジエン誘導体、ペリレン誘導体などが挙げられ、また、金属キレート化オキシニド化合物(特開昭59-194393)も使用できる。

【0036】陰極材料は、仕事関数の小さい銀、銅、マグネシウム、アルミニウム、カルシウム、あるいはこれらの合金が用いられる。また、アルミニウムやゲルマニウムをドーパした酸化亜鉛も透明な陰極として利用できる。陽極と陰極の少なくとも一方は素子の発光波長域で十分に透明であることが望ましい。

【0037】本発明に係る有機薄膜発光素子は、図1に示されるように、以上の各層をガラス基板やシリコンなどの半導体基板上に順次積層することで素子として構成される。これらは、素子の安定性、特に大気中の水分に対する保護のために、シリコンオイル等と一緒にガラスセルに封入するようによい。

【0038】尚、本発明に係る有機薄膜発光素子は、図1に示される構造に限られるものではなく、必要により図6、7、8、9に示されるような構造とすることもできる。

【0039】以下、本発明に係る有機薄膜発光素子の具体例を実施例によりさらに詳細に説明する。

【0040】

【実施例】

実施例1. 本実施例では、金属酸化物薄膜の作製方法及その特性について示す。

【0041】表1に示された各材料を使用してガラス基板上に高周波マグネトロンスパッタ法により金属酸化物薄膜を形成した。この金属酸化物薄膜の形成条件及び特性が表2に示される。

【0042】

【表2】

金属酸化物 薄膜	成膜条件		典型的組成	膜厚 (Å)	抵抗率 (Ωcm)	光透過率 (%)
	ターゲット	スパッタガス				
RuOx	Ru	Ar(70%) + O ₂ (30%)	RuO _{1.92}	3680	2.7×10^{-4}	10
MoOx	MoO ₃	Ar	MoO ₃	2150	1.2×10^{-2}	10
VOx	V ₂ O ₅	Ar	VO _{2.22}	1320	10^5	20
ITO	ITO(5wt%SnO ₂)	Ar(99%) + O ₂ (1%)		1720	3.3×10^{-4}	90

基板温度は150℃で、スパッタガス圧は 2×10^{-3} Torr (0.27 Pa)とした。酸化モリブデン薄膜と酸化ルテニウム薄膜が高い導電性を示し、酸化バナジウム薄膜は半導体的であった。これらの金属酸化物薄膜は着色しており、表2に示されるように可視域での光の透過率が低いので、上述の通りITOとともに2層構造とするのが好ましい。表2には、各金属酸化物薄膜の典型的な組成も参考として示される。この組成は、スパッタ成膜の条件(ガスの圧力、ガスの種類)によって若干変動する。

【0043】表3には、ITOと前述の金属酸化物薄膜とを積層した、図2に示されるような2層構造電極の導電性と光透過率が示される。金属酸化物薄膜の膜厚は透明性を高めるために、300オングストローム以下にした。また、ITOの膜厚は1200オングストロームとした。

【0044】本実施例の場合、電極を2層構造とすることで、その表面抵抗は約25 Ω /□に設定することができた。また、光透過率は、表2に示された各金属酸化物薄膜の値よりも向上させることができた。

【0045】

【表3】

透明電極	表面抵抗 (Ω /□)	透過率 (%)
RuOx/ITO	22.5	60
MoOx/ITO	29.1	40
VOx/ITO	33	60
ITO	20	90

実施例2. 本実施例では、図1に示される構造の有機薄膜発光素子を作製し、その特性を評価した。

【0046】ガラス基板上に実施例1の方法により約1500オングストロームの酸化バナジウム薄膜からなる陽極を形成した。その陽極上に、真空蒸着法により、真空度約 2×10^{-7} Torr (2.7×10^{-5} Pa)、蒸着速度約30オングストローム/分の条件でTPDを約500オングストローム形成し、正孔輸送層とした。発光層としてはアルミキノリノール錯体を用いた。陰極と

光層を約500オングストローム、MgAg電極を約1800オングストローム成膜して有機薄膜発光素子を作製し、実施例8と同様に発光開始電圧と発光効率を測定した。

【0056】表4に示されるように、この素子の発光開始電圧は3.5Vであった。また、5V印加で30cd/m²の輝度を観察した(図4)。発光効率は0.85lm/Wであった。

【0057】本実施例においては、酸化ルテニウムの膜厚をさらに薄くすれば電極の光透過率が改善され、効率がさらに向上する。

【0058】実施例5. ガラス基板上に、1200オングストロームのITOと300オングストロームの酸化モリブデンを連続成膜した2層構造電極を形成し、その上に実施例2と同様に、正孔輸送層、発光層、電極を真空蒸着して有機薄膜発光素子を作製し、実施例3と同様に発光開始電圧と発光効率を測定した。

【0059】表4に示されるように、この素子の発光開始電圧は3.5Vで、印加電圧5Vでは30cd/m²の輝度を示した(図5)。

【0060】実施例6. 次に、上部電極(陰極)から、光を取り出す場合の素子についての実施例を示す。

【0061】図3には、本実施例に係る有機薄膜発光素子の断面図が示される。図3において、ガラス基板10上に、酸化ルテニウムを1500オングストローム成膜して陽極12とし、その上に、実施例2と同様に、正孔輸送層18と発光層16とを真空蒸着した。最後に、陰極14として、仕事関数の小さなアルミ添加酸化亜鉛を高周波スパッタ法で約1200オングストローム成膜した。

【0062】この素子で、酸化ルテニウム電極(陽極12)に正の電圧を印加し、酸化亜鉛電極(陰極14)を通して光を観測したところ、透明な陰極14側から明瞭

な発光が観察された。この場合、酸化ルテニウム電極が黒色であるためMgAg金属電極の場合よりもコントラスト比の高い発光が得られた。

【0063】

【発明の効果】以上説明したように、本発明によれば、金属酸化物薄膜電極と正孔輸送層あるいは発光層とのエネルギー障壁を小さくでき、正孔輸送層や発光層への正孔注入が容易となり、低い印加電圧で素子駆動が可能となる。その結果、発光効率が改善され、素子の長寿命化が達成できる。よって、本発明の発光素子は各種ディスプレイ分野への応用が可能となる。

【図面の簡単な説明】

【図1】 本発明に係る有機薄膜発光素子の断面図である。

【図2】 本発明に係る2層構造電極の断面図である。

【図3】 本発明に係る陰極から光を取り出す有機薄膜発光素子の断面図である。

【図4】 各種素子の駆動時間に対する発光輝度の変化を示す図である。

【図5】 各種素子の印加電圧と発光輝度との関係を示す図である。

【図6】 単層構造の有機薄膜発光素子の断面図である。

【図7】 正孔輸送層を有する2層構造有機薄膜発光素子の断面図である。


【図8】 電子輸送層を有する2層構造有機薄膜発光素子の断面図である。

【図9】 3層構造の有機薄膜発光素子の断面図である。


【符号の説明】

10 基板、12 陽極、14 陰極、16 発光層、18 正孔輸送層、20 電子輸送層、22 ITO層、24 金属酸化物薄膜。


【図1】




【図2】




【図3】




【図4】




【図5】




【図6】



【図9】



【図7】



【図8】

